


Freq	Size	VarCoeff	M1332	M1333
10	0.4	1.8	0.4	0.4
50	2.4	1.7	2.5	2.4
90	10.9	4.7	11.4	10.4



Schweiss-Stahlstaub

Meas.Nr. 1332 Date 03.19.2009 13:35

Personal Report No.:

Material Schweiss-Stahlstaub


090062

Description

Calculation Fraunhofer automatic TradeOff 6.456542e+002
 Scans Fine 100 Scans Coarse 0 Channels 51 Beam Obscuration 12.00 %
 Meas. Range 0.08 [µm] - 42.30 [µm] Pump 8 Ultrasonics 3

Freq	Size
5	0.3
10	0.4
15	0.6
20	0.7
25	0.9
30	1.1
40	1.6
50	2.5
60	3.8
70	5.6
80	7.9
85	9.4
90	11.4
95	14.4
99	19.7

Freq	Size
0	0.1
12.6	0.5
15.3	1
16.9	2
22.3	5
19.6	10
9	15
3.5	20
0.9	30
0	40
0	50
0	60
0	70
0	80
0	100



Meas.Nr. 1333 Date 03.19.2009 13:35

Personal Report No.:

Material Schweiss-Stahlstaub

090062

Description

Calculation Fraunhofer automatic TradeOff 1.862087e+003
 Scans Fine 100 Scans Coarse 0 Channels 51 Beam Obscuration 12.00 %
 Meas. Range 0.08 [µm] - 42.30 [µm] Pump 8 Ultrasonics 3

Freq	Size
5	0.3
10	0.4
15	0.5
20	0.7
25	0.9
30	1
40	1.6
50	2.4
60	3.6
70	5.1
80	7.1
85	8.5
90	10.4
95	13.3
99	18.4

Freq	Size
0	0.1
13.3	0.5
15.5	1
16.7	2
24	5
19.6	10
7.7	15
2.8	20
0.4	30
0	40
0	50
0	60
0	70
0	80
0	100

