

Meas. No. 6713 SOP 45 Date 21.04.2009 10:35:58 Operator: FRITSCHLAN\Benes

Material: **Frit Glass L125**

**P7pr.I. 0,5mm 180min**

Description: water + 30s ultrasonic + 0.1% Na4P2O7

Calculation Automatische Modellerkennung

Mode Wet

Serial No. 22.2000.00/90771

Beam absorption 13,1 %

Pump 70,00 %

Meas. range 0,10  $\mu\text{m}$  - 53,10  $\mu\text{m}$

Cellposition 1

Channels 51

Ultrasonic On

Scans 100

Prot.-No.: **090067**

5-99%

Obere Kornklasse [ $\mu\text{m}$ ]	Q3(x) [%]
0,152	5,0
0,181	10,0
0,208	15,0
0,233	20,0
0,260	25,0
0,288	30,0
0,317	35,0
0,349	40,0
0,384	45,0
0,422	50,0
0,464	55,0
0,511	60,0
0,563	65,0
0,625	70,0
0,699	75,0
0,789	80,0
0,906	85,0
1,074	90,0
1,356	95,0
1,996	99,0

0.1-5 $\mu\text{m}$  (12 values)

Obere Kornklasse [ $\mu\text{m}$ ]	Q3(x) [%]
0,100	1,5
0,300	32,2
0,500	58,9
1,000	88,0
1,500	96,5
2,000	99,0
2,500	99,8
3,000	99,9
3,500	100,0
4,000	100,0
4,500	100,0
5,000	100,0

