

Meas. No. 6584 SOP 45 Date 09.04.2009 14:35:15 Operator: FRITSCHLAN\Benes

Material: **Frit Glass L125** **3 mm 30 min**

Description: water + 0.1% Na4P2O7 + ultrasonic 30 sec

Calculation Automatische Modellerkennung

Mode	Wet	Serial No.	22.2000.00/90771
Beam absorption	12,4 %	Pump	90,00 %
Meas. range	0,10 µm - 199,14 µm	Cellposition	2
Channels	102	Ultrasonic	On
Scans	100	Prot.-No.:	<b>090067</b>

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,173	5,0
0,283	10,0
0,432	15,0
0,605	20,0
0,781	25,0
0,959	30,0
1,136	35,0
1,318	40,0
1,509	45,0
1,712	50,0
1,937	55,0
2,191	60,0
2,485	65,0
2,846	70,0
3,305	75,0
3,931	80,0
4,921	85,0
6,656	90,0
9,522	95,0
14,132	99,0

01-30µm

Obere Kornklasse [µm]	Q3(x) [%]
0,120	1,7
0,200	6,4
0,300	10,6
0,500	17,0
1,000	31,2
1,500	44,8
2,000	56,3
3,000	71,8
4,000	80,4
5,000	85,3
6,000	88,4
7,000	90,8
8,000	92,6
9,000	94,3
10,000	95,6
15,000	99,3
20,000	100,0
25,000	100,0
30,000	100,0

