

Meas. No. 6597 SOP 45 Date 14.04.2009 09:05:39 Operator: FRITSCHLAN\Benes

Material: **Frit Glass L125** **3 mm 60 min**

Description: water + 0.1% Na4P2O7 + ultrasonic 30 sec

Calculation Automatische Modellerkennung

Mode Wet Serial No. 22.2000.00/90771

Beam absorption 14,2 % Pump 65,00 %

Meas. range 0,10 µm - 199,14 µm Cellposition 2

Channels 102 Ultrasonic On

Scans 100 Prot.-No.: **090067**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,202	5,0
0,344	10,0
0,481	15,0
0,615	20,0
0,748	25,0
0,886	30,0
1,031	35,0
1,186	40,0
1,353	45,0
1,536	50,0
1,741	55,0
1,975	60,0
2,250	65,0
2,582	70,0
3,020	75,0
3,584	80,0
4,464	85,0
6,023	90,0
9,151	95,0
14,912	99,0

01-30µm

Obere Kornklasse [µm]	Q3(x) [%]
0,120	1,4
0,200	4,9
0,300	8,4
0,500	15,7
1,000	33,9
1,500	49,1
2,000	60,5
3,000	74,8
4,000	82,6
5,000	87,1
6,000	89,9
7,000	92,0
8,000	93,5
9,000	94,8
10,000	95,9
15,000	99,0
20,000	99,9
25,000	100,0
30,000	100,0

