

Meas. No. 6683 SOP 45 Date 17.04.2009 11:24:56 Operator: FRITSCHLAN\Benes

Material: **Frit Glass L125** **5 mm 120 min**

Description: water + 0.1% Na4P2O7 + ultrasonic 30 sec

Calculation Automatische Modellerkennung

Mode Wet

Serial No. 22.2000.00/90771

Beam absorption 11,6 %

Pump 40,00 %

Meas. range 0,10 µm - 53,10 µm

Cellposition 1

Channels 51

Ultrasonic On

Scans 100

Prot.-No.: **090067**

5-99%

Obere Kornklasse [µm]	Q3(x) [%]
0,319	5,0
0,473	10,0
0,616	15,0
0,760	20,0
0,909	25,0
1,069	30,0
1,240	35,0
1,428	40,0
1,636	45,0
1,871	50,0
2,133	55,0
2,461	60,0
2,841	65,0
3,303	70,0
3,886	75,0
4,693	80,0
5,802	85,0
7,521	90,0
10,468	95,0
16,330	99,0

01-30µm

Obere Kornklasse [µm]	Q3(x) [%]
0,120	0,3
0,200	1,8
0,300	4,4
0,500	10,9
1,000	27,9
1,500	41,8
2,000	52,5
3,000	66,8
4,000	75,9
5,000	81,6
6,000	85,7
7,000	88,7
8,000	91,0
9,000	92,9
10,000	94,4
15,000	98,5
20,000	99,7
25,000	100,0
30,000	100,0

