


Meas.Nr. 59903 **Date** Montag, 21 Januar 2013 03:11 **Personal Report No.:**
Material A9427-3 **M130008**
Description dispersed in water + 0,1% Na₄P₂O₇, 30s ultrasonic

Calculation Fraunhofer very_broad **TradeOff** 1,000000e+005
Scans Fine 100 **Scans Coarse** 100 **Channels** 102 **Beam Obscuration** 14,00 %
Meas. Range 0,08 [µm] - 2000,00 [µm] **Pump** 6 **Ultrasonics** 10

%	< µm
5	0,68
10	1,07
15	1,52
20	2,10
25	2,89
30	4,08
40	8,91
50	16,00
60	23,45
70	31,92
80	42,92
90	60,14
95	76,03
98	94,71
99	107,25

%	< µm
0,1	0,10
2,6	0,50
9,1	1,00
19,3	2,00
32,7	5,00
41,6	10,00
55,5	20,00
67,9	30,00
77,7	40,00
84,8	50,00
89,9	60,00
95,9	80,00
98,5	100,00
99,5	120,00
100,0	150,00



▲ 59903 dQ3(x) — 59903 Q3(x)