


Meas.Nr. 59901 **Date** Montag, 21 Januar 2013 02:49 **Personal Report No.:**
Material Sample 1: p-6 650rpm, 1min, 500ml ZrO2 **M130008**
Description dispersed in water + 0,1% Na4P2O7, 30s ultrasonic

Calculation Fraunhofer very_broad **TradeOff** 1,000000e+005
Scans Fine 100 **Scans Coarse** 100 **Channels** 102 **Beam Obscuration** 17,00 %
Meas. Range 0,08 [µm] - 2000,00 [µm] **Pump** 6 **Ultrasonics** 10

%	< µm
5	0,62
10	0,94
15	1,30
20	1,74
25	2,30
30	3,02
40	5,40
50	9,67
60	15,43
70	22,40
80	31,44
90	45,67
95	58,67
98	74,47
99	85,09

%	< µm
0,0	0,10
3,2	0,50
10,9	1,00
22,5	2,00
38,7	5,00
50,6	10,00
66,8	20,00
78,7	30,00
86,8	40,00
92,0	50,00
95,4	60,00
98,6	80,00
99,7	100,00
100,0	120,00
100,0	150,00



▲ 59901 dQ3(x) — 59901 Q3(x)