


Meas.Nr. 60861 **Date** Donnerstag, 14 Februar 2013 02:15 **Personal Report No.:**
Material Cement P6cl 650rpm 80ml ZrO2 20mm 5min **M130022**
Description predisp in IPA . 1min Ultrasound LABORETTE 17 meas. in 0,1% Na4P2O7

Calculation Fraunhofer broad **TradeOff** 1.000000e+003
Scans Fine 100 **Scans Coarse** 100 **Channels** 102 **Beam Obscuration** 15.00 %
Meas. Range 0.08 [µm] - 2000.00 [µm] **Pump** 6 **Ultrasonics** 10

%	< µm
5	0.81
10	1.49
15	2.37
20	3.59
25	5.22
30	7.17
40	11.46
50	16.13
60	21.20
70	27.03
80	33.98
90	43.77
95	51.80
98	60.87
99	66.77

%	< µm
0.0	0.1
2.3	0.5
6.5	1.0
24.4	5.0
36.7	10.0
47.7	15.0
57.7	20.0
74.5	30.0
86.7	40.0
94.1	50.0
97.8	60.0
99.4	70.0
99.9	80.0
100.0	90.0
100.0	100.0



▲ 60861 dQ3(x) — 60861 Q3(x)