

Meas.Nr. 67790 Date 09.17.2013 08:14 Personal Report No.:

Material B.Clay in IPA 60min P7pl 80ml ZrO2 0,1mm **M130240**

Description predisp. in Benzine with 1 min ultrasonic LABORETTE 17; meas. in Benzine


Calculation Mie n = 1.45000 -i 0.30000 **broad TradeOff** 1.000000e+002

Scans Fine 100 Scans Coarse 0 Channels 108 **Beam Obscuration** 14.00 %

Meas. Range 0.01 [µm] - 42.30 [µm] Pump 3 **Ultrasonics** 3

%	< µm
5	0.012
10	0.020
15	0.050
20	0.061
25	0.070
30	0.079
40	0.096
50	0.115
60	0.138
70	0.166
80	0.207
90	0.282
95	0.373
98	0.560
99	0.839

%	< µm
42.16	0.10
78.53	0.20
91.36	0.30
95.86	0.40
97.51	0.50
98.23	0.60
98.63	0.70
98.91	0.80
99.13	0.90
99.31	1.00
99.59	1.20
99.84	1.50
99.97	2.00
100.00	2.50
100.00	3.00



▲ 67790 dQ3(x) — 67790 Q3(x)